



* C, S は、精度の観点から、赤外線吸収法を採用した。

相対感度係数値の比較

	本測定値	メーカー値
C	5.116	5.021
Si	2.023	1.846
P	3.537	3.159
S	3.747	3.903
Cr	2.154	2.210
Mn	1.353	1.459
Co	0.896	1.096
Ni	1.306	1.505
Cu	5.569	5.144
Mo	1.215	1.119

Fig. A 日本鉄鋼標準試料認証値による GDMS の相対感度係数 (RSF) 補正